



High Quality Decorative Protective Sealers.

DESCRIPTION & USE

Multicoat's ACRATHANE COLORSEAL consists of a series of high quality waterbase modified resins that provide a high quality, durable seal on masonry, cementitious, and other building substrates. Colors are factory blended to insure uniformity.

ACRATHANE COLORSEAL is designed for application to a variety of Multicoat's Systems, most notably the KRETE KOTE System. It provides a tough, color consistent, durable and wear resistant protection to surfaces subject to heavy foot and moderate vehicular traffic. Ideally suited for pool decks.

ACRATHANE CLEARSEAL is also a water base material. Not typically used in Colorseal applications, however it can be used to achieve a glossy, wet look. Is also used in conjunction with MULTI-STAIN to lock in the color. CLEARSEAL can also be used on most masonry and stone substrates.

ADVANTAGES:

- Long Wearing
- Enhances Appearance
- Easy to Clean
- Multiple Color Availability
- Weather Resistant
- Water Base - Green Friendly
- Ideal for Re-Sealing Old Kool-Deck
- Chemical Resistant for Pool Decks

SEE TEST DATA

SURFACE PREPARATION

Substrate must be structurally sound and free from grease, oil, dirt, dust, sealers, water repellents and other foreign materials which may interfere with proper bonding. Surface must be completely dry prior to COLORSEAL or CLEARSEAL application.

Multicoat KRETE KOTE and TOP COAT must be allowed to set up and cure for at least 24 to 48 hours before COLORSEAL application. New concrete should be allowed to cure for a minimum of 20 days, and be free from curing compounds, release agents if any, and other water repellent materials which may prevent proper bonding. Do not use on treated lumber.



ONE GALLON CANS
FIVE GALLON PAILS



APPLY DILUTED FIRST COAT OF
ACRATHANE COLORSEAL WITH ROLLER.



SECOND COAT (FULL STRENGTH COAT)
CAN BE APPLIED BY AIRLESS SPRAYER
OR ROLLER.



CLEARSEAL GOES ON WHITE AND
DRIES TO A CLEAR FILM IN MINUTES.
CAN BE ROLLED OR SPRAYED.

ACRATHANE COLORSEAL / CLEARSEAL



COLORSEAL APPLICATION

Multicoat COLORSEAL must be applied in two coats.

First Coat: Mix COLORSEAL to uniformity with slow speed mixer. With continuous mixing add clean water in ratio of 1 part water to 3 parts COLORSEAL. Apply diluted COLORSEAL with nap roller with very firm pressure. (1/2" nap roller for smooth and 3/4" nap roller for rough surfaces). Allow a minimum of one (1) hour to dry.

Second Coat: Mix to uniformity only. Apply with firm pressure. DO NOT APPLY THICKER THAN RECOMMENDED. Airless sprayers may be used for the final coat. Allow final coat a minimum of 24 hours before placing area into use. Will fully cure in 14 days, during which care should be exercised against excessive abuse. **Each pail has a 'lot' number. Do not mix lot numbers during the final coat. If more than one lot number must be used, box the material to insure color uniformity.**

CLEARSEAL APPLICATION

Mix to uniformity with slow speed mixer. DO NOT DILUTE CLEARSEAL, use as packaged. One coat application is recommended for a semi-gloss appearance. Two coats will have a shiny gloss appearance. Clear Seal goes on white and dries clear.

LIMITATIONS

Do not apply if substrate temperature is below 40°F or above 100°F, or if ambient temperature below 40°F above 100°F.

Do not apply if precipitation is expected within a twenty four (24) hour period.

COVERAGE

ACRATHANE COLORSEAL and CLEARSEAL: 200 - 300 sq. ft. per gallon depending on surface texture, porosity and method of application.

PACKAGING AND STORAGE

COLORSEAL and CLEARSEAL: Furnished in 1 gallon cans and 5 gallon Pails. Shelf life approximately 18 months in unopened containers. Store at 40° to 90° F in a dry environment.

DAMAGE LIMITATION

Seller shall not be liable for any damages, injury, loss, direct or consequential, resulting from its products. The parties intend that the limitation of damages, including consequential damages, applies even if the exclusive remedy provided for herein fails of its essential purpose.

EXCLUSIVE REMEDY

Seller's sole obligation, and buyer's exclusive remedy shall be to replace material if found to be defective.

WARRANTY DISCLAIMER

There are no warranties which extend beyond the description of the fact hereof. Seller expressly disclaims all other warranties regarding the use of its products, whether expressed or implied, including the implied warranties of merchantability and for fitness of a particular purpose. Since use of the product is beyond the Seller's control, the Buyer assumes all risk of use.

WARRANTY

Materials are guaranteed with respect to uniformity and quality within manufacturer's specifications.

TEST DATA - ACRATHANE COLORSEAL/CLEARSEAL

TEST	METHOD	RESULTS	TEST RESULTS KEY
1. Chemical Resistance Test	ASTM D2299		
	Turpentine	1	1. Unaffected
	Gasoline	1	2. Superficial Affect (Will need to be cleaned.)
	Paint Thinner	1	3. Considerable Affect (May have to re-seal)
	Lubricating Oil	1	
	Sulfuric Acid—3%	2	
	Hydraulic Fluids	3	
	Toluene	1	
	Salt Solution 20%	1	
	Muratic Acid 10%	1	
	Prestone Coolant	1	



MULTICOAT® CORPORATION West Coast

Toll Free: (877) 685-8426
(949) 888-7100 Fax (949) 888-2555
Website: www.multicoat.com
E-mail: info@multicoat.com

MULTICOAT® PRODUCTS, INC. East Coast

Toll Free: (800) 660-6729
(304) 586-0616 Fax (304) 586-0620
Website: www.multicoat.com
E-mail: info@multicoat.com

AVAILABLE THROUGH

MC311

The Coating of the Future... Today