



ULTRA PRO 2000

- *Commercial synthetic rubber coating*
- *For use on previously painted chlorinated or synthetic rubber surfaces, as well as bare concrete*
- *Self-priming, two-coat system*
- *Up to 2 years of service life*
- *VOC Compliant in Canada and the US (except California)*

AVAILABLE IN THESE COLORS



WHITE
311



DAWN BLUE
328



ROYAL BLUE
329

Note: Color differences may occur between actual color chips shown.

COMMERCIAL SYNTHETIC RUBBER AQUATIC COATING

Ramuc Ultra Pro 2000 Synthetic Rubber Coating is VOC compliant in Canada and the US (except California). It is designed for commercial use where a competitively priced paint is required and pool maintenance is performed every few years. This coating is an excellent choice for recoating previously painted chlorinated rubber and synthetic rubber surfaces.

TECHNICAL INFORMATION

VEHICLE TYPE: Synthetic Rubber

FINISH: Flat

COMPONENTS: 1

CURING MECHANISM: Air Dry

SOLIDS BY VOLUME: 35 ± 1%

SOLIDS BY WEIGHT: 57% ± 2%

COVERAGE: 175 – 200 sq. ft. on bare surface; up to 300 sq. ft. on recoats

VOC: 325 g/l max (as supplied)

FLASH POINT: 84° F (SETA)

APPLICATION METHOD: 3/8" Mohair or Lambskin Roller, Airless or Conventional Spray

DRY FILM THICKNESS PER COAT: 1.0 mils (3.0 mils wet)

APPLICATION TEMP: 50° F min/90° F max

NUMBER OF COATS: 2 (product is self-priming)

RECOAT TIME: Indoor/Outdoor pool – min. overnight to 24 hrs.

DRY TIME: Outdoor Pool: 5-7 days before filling. Indoor Pool: 10-14 days before filling. Use adequate ventilation.

NOTE: NOT FOR USE ON BARE FIUBERGLASS/GELCOAT. DO NOT USE IN HOT TUBS OR SPAS.



COMPATIBILITY: For compatibility purpose, the existing paint on previously painted surfaces of a pool should be determined before painting. **Use dark colors for accent painting only. Dark colors can prematurely fade or blister, especially in chemically treated water.**

SURFACE REPAIRS AND JOINT/CRACK FILLER: Plaster or concrete for previously painted surfaces should be tested for integrity and soundness. Aged plaster should be checked for integrity. Check for hollow or weak/crumbling plaster by using a ball-peen hammer or any other comparable method. Perform repairs on the plaster before painting. Any minor repairs needed to be made, such as patching with hydraulic cement or filling of cracks, should be done and allowed to cure prior to surface prep. We suggest using Vulkem polyurethane sealant. Vulkem must be top-coated before being submersed in chemically treated water.

SURFACE PREPARATION: Coating performance, in general, is proportional to the degree of surface preparation. Follow recommendations carefully, avoiding shortcuts. Inadequate preparation of surfaces will virtually assure inadequate coating performance. We recommend using Ramuc Clean & Prep Solution™. Ramuc Clean & Prep Solution degreases and dissolves mineral deposits and increases porosity to create maximum adhesion. Unlike all other acid-based materials, Ramuc Clean & Prep Solution neutralizes via water and is safe to use near plants and grass. If surface is exceptionally hard, we recommend sanding with an #80 grit sandpaper to create surface profile prior to applying the first coat of Ultra Pro 2000. Follow package directions carefully. New concrete and plaster surfaces must be cured for 28 days prior to painting.

CONDENSATION TEST: After all cleaning is complete, allow the surface to dry. Average time varies according to climate and porosity of the substrate. 1) Tape 2' x 2' pieces of transparent plastic to areas in the deep end wall, floor and several other areas of the pool. 2) Wait about 4 hours to determine if condensation has formed underneath the plastic. 3) If condensation is evident, the surface is not dry enough to paint. 4) Remove the plastic and wait 24 hours to perform the test again and continue until no condensation forms. This ensures that the surface is dry enough to apply paint.

APPLICATION: Use no thicker than a 3/8" nap roller used for solvent based paints. DO NOT use rollers with cardboard cores. Apply at the recommended coverage rate. Ideal air temperatures for application are between 50° and 90° F. Surface temperature should be at least 50° F, no more than 90° F. Overnight curing temperatures must be at least 50° F or the paint will not cure properly. Do not paint when rain is imminent. New concrete and plaster surfaces must be cured a minimum of 28 days prior to painting.

MIXING THE PAINT: Ultra Pro 2000 Chlorinated Rubber Coating is self-priming; no other type of primer is recommended or should be used. Mechanically mix the paint to achieve uniform consistency and color. If more than one gallon of paint is used at a time, box (intermix) several gallons together.

SPRAY INFORMATION: Airless: 2000-2500 P.S.I. TIP SIZE: .013 - .017 (0.33 - .043 mm)

CLEAN UP: Ramuc Thinner
