



POOL AND DECK COATINGS

Kelley Technical Coatings



Louisville, Kentucky 40201-3726
[502] 636-2561 [800] 458-2842
Fax [502] 635-5170 www.kelleytech.com

ALL OLYMPIC PRODUCTS ARE VOC COMPLIANT

Bulletin No. 107

PATIO TONES Water-Base Non-Slip Coating for Pool Decks and Sprayed Concrete Surfaces

PATIO TONES deck coatings are lightly textured, slip resistant top coatings specifically formulated for use on concrete pool decks and patios. They are available in eight colors.

One big advantage to using PATIO TONES on a deck finish is that you may coat over cracked or broken concrete that has been repaired thereby concealing any substrate damage.

PATIO TONES has been tested for durability and bonding strength under the most severe conditions and has proven to be a high quality, low cost way to improve the appearance of concrete pool decks and patio areas. Because PATIO TONES is water-based, it can be applied to wet concrete.

DIRECTIONS FOR USE

Surface must be free of grease, suntan oil, body oil, dirt and foreign matter. First sweep the area vigorously to remove all loose material. Then, scrub with a solution of tri-sodium phosphate, or Olympic No. 910 POOL WASHING COMPOUND at a ratio of eight ounces to one gallon of water. This will remove oils which prevent adhesion. Hose off immediately with water. At that point, it is best to acid wash the surface with 10% solution of muriatic acid. This creates pores to allow adhesion. Hose off, and then repeat the tri-sodium phosphate procedure to neutralize any remaining acid. If not neutralized, acid-salts will form and impede PATIO TONES performance. Hose off one last time.

FIRST COAT: Surface may be wet but do not roll PATIO TONES through standing water or "puddles". On bone dry surfaces thin one pint per gallon with water. Use a 1/2" nap roller cover on smooth surfaces. Use a 3/4" nap roller cover on rougher surfaces. Flow on slowly and evenly. Avoid overspreading. Do not apply when air or surface temperature is under 50°F. Avoid rolling during a very hot, midday sun.

DRYING TIME: May be recoated in four hours in warm weather 80°F or above. Longer in cooler weather. PATIO TONES should be given 24 hours curing time before foot traffic is allowed.

COVERAGE: Average 90 to 125 square feet per gallon, depending on the porosity of the surface.

CLEAN UP: Clean application equipment with water immediately after use.

PREVIOUSLY COATED SURFACES

PATIO TONES will adhere to most other finishes; however, any glossy areas should be sanded before recoating. Any peeling or flaking paint must also be removed before recoating. Do not apply over epoxy.

PHYSICAL DATA

COVERAGE: First Coat - 80 to 100 square feet (7.4 to 9.3 sq. meters) per gallon depending on the porosity of the surface

SECOND COAT: Average 125 square feet (12 sq. meters) per gallon

DRY TIME: Set to touch in 1 hour

RECOATING TIME: 4 hours over 80°F (28°C)
Overnight under 80°F (28°C)

READY FOR FOOT TRAFFIC: 24 hours

SOLVENT AND CLEAN UP: Water

PACKAGING: Gallons and 5 gallon containers

KEEP OUT OF THE REACH OF CHILDREN!
Water-based - KEEP FROM FREEZING

WARNING!

If you scrape or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at **1-800-424-LEAD** or log on to **www.epa.gov/lead**

NOTE: KELLEY TECHNICAL COATINGS, INC. makes no implied warranty of merchantability, no implied warranty of fitness for a particular purpose and no other warranty, either express or implied, concerning its products.

KELLEY TECHNICAL COATINGS, INC.
Louisville, KY 40210