



## AFW 8000

### ADHESIVE SYSTEM

#### TECHNICAL DATA

##### Product Description

AFW 8000 was developed to mix, apply, and cure underwater. This product is a very versatile adhesive that will work on most applications. AFW 8000 is commonly used to repair vinyl pool liners, fiberglass, light rings, skimmers, main drains, concrete, pool tile and hose repairs. This compound is paintable and sandable.

UNCURED PROPERTIES*		
Property	Value	Test Method
Solvent Content	No Nonreactive Solvents	N/A
Chemical Class, PT A	Epoxy	N/A
Chemical Class, PT B	Amine	N/A
Color, PT A	White	N/A
Color, PT B	Light Yellow	N/A
Specific Gravity, PT A	1.22	QPTTEST002
Specific Gravity, PT B	0.99	QPTTEST002
Viscosity @ 25C, cps, PT A	60,000-90,000	QPTTEST001
Viscosity @ 25C, cps, PT B	70,000-90,000	QPTTEST001

CURED MECHANICAL PROPERTIES*		
Property	Value	Test Method
Moisture Resistance	Excellent	N/A
Operating Temperature Range, C	-20 - 120	N/A

CURE OVERVIEW*		
Property	Value	Test Method
Mix Ratio by Volume, PT B:A	2:1	N/A
Pot Life @ room temperature, min	80	N/A
Cure Time @ room temperature, hr	5-8	N/A

##### Storage:

Store material in cool, dry location at a temperature between 10°C to 28°C. Keep from freezing. Refer to packaging specific quote for shelf life information. Consult MSDS for safe handling recommendations.

Revision Number: 1 - New      Date: 15 December, 2015

AquaBond, LLC 6444 E Spring St #275, Long Beach, CA 90815 www.aquabondadhesives.com Phone 714-961-1420

*AquaBond, LLC makes no express or implied warranties or merchantability, fitness or otherwise with respect to this product. In addition, while the information contained herein is believed to be reliable, no warranty is express or implied regarding the accuracy of the results to be obtained from the use thereof. The properties given are typical values and are not intended for use in preparing specifications. User should make their own test to determine the suitability of this product for their own purposes.*